SWFR X4

Very-thin-wall, highly flame-retardant, zero halogen, metric-sized heat-shrinkable tubing

SWFR X4 heat-shrinkable tubing is a cost-effective, environmentally friendly choice for many commercial applications. SWFR X4 tubing is a very-thin-wall version of SWFR, a specially formulated polyolefin with low recovery temperature, excellent flexibility, and high flame-retardance (VW-1).

SWFR X4 tubing is typically applied where space savings is important, offering the ability to pack components more closely than is possible with standard tubings. SWFR X4 tubing can shrink more than twice as fast as standard products. This rapid shrinking may be important in the prevention of overheating of temperature-sensitive components.

Unlike other typical flame-retardant tubings, SWFR X4 tubing is halogen free.

SWFR X4 products are UL-recognized at 125°C, 300 V, and CSA-certified at 125°C, 300 V, with UL VW-1 and CSA OFT flame-retardancy ratings.

| Temperature rating | |
|-----------------------------------|-----------------|
| Minimum shrink temperature: | 70°C |
| Full recovery temperature: | 90°C |
| Continuous operating temperature: | - 30°C to 125°C |

| Specifications* | ations* | | ⑤ ₽° |
|-----------------|---------|--------|-------------|
| Туре | Raychem | UL | CSA |
| SWFR X4 | SWFR X4 | E35586 | LR31929 |

^{*}When ordering, always specify latest issue.



| | As supplied | | Fully recove | Fully recovered | |
|------|----------------|-----------|--------------|-----------------|--|
| | D | Wall | d (max.) | W (min.) | |
| | Inside | thickness | Inside | Wall | |
| Size | diameter | (nominal) | diameter | thickness** | |
| 0.8 | 1.2 ± 0.25 | 0.1 | 0.4 | 0.25 | |
| 1.0 | 1.4 ± 0.25 | 0.1 | 0.5 | 0.25 | |
| 1.5 | 1.9 ± 0.25 | 0.1 | 0.75 | 0.25 | |
| 2.0 | 2.3 ± 0.25 | 0.1 | 1.0 | 0.26 | |
| 2.5 | 2.8 ± 0.25 | 0.15 | 1.25 | 0.28 | |
| 3.0 | 3.3 ± 0.25 | 0.15 | 1.5 | 0.28 | |
| 3.5 | 3.8 ± 0.25 | 0.15 | 1.75 | 0.28 | |

| | As supplied | | Fully recovered | |
|------|---------------|-----------|-----------------|-------------|
| | D | Wall | d (max.) | W (min.) |
| | Inside | thickness | Inside | Wall |
| Size | diameter | (nominal) | diameter | thickness** |
| 4.0 | 4.4 ± 0.25 | 0.15 | 2.0 | 0.28 |
| 6.0 | 6.5 ± 0.4 | 0.15 | 3.0 | 0.33 |
| 9.0 | 9.5 ± 0.4 | 0.15 | 4.5 | 0.33 |
| 13.0 | 13.7 ± 0.5 | 0.2 | 6.5 | 0.41 |
| 18.0 | 19.2 ± 0.6 | 0.2 | 9.0 | 0.46 |
| 25.0 | 26.4 ± 1.0 | 0.2 | 12.5 | 0.46 |
| | | | | |

 $[\]ensuremath{^{**}}\xspace$ Wall thickness will be less if tubing recovery is restricted during shrinkage.

| Ordering information | | | | |
|----------------------|-----------------|---|--|--|
| Colors | Standard | Black | | |
| Size selection | Always order th | Always order the largest size that will shrink snugly over the component being covered. | | |
| Standard packaging | On spools | | | |
| Marking | Not marked. UL | ., CSA, and Japan -F- Mark on labels. | | |
| Ordering description | Specify product | name and size; for example, X4 2.0 | | |

Specification values

| | Property | Unit | Requirement | Method of test |
|------------|---|-------------------|--|----------------|
| Physical | Dimensions | mm | See reverse | ASTM D 2671 |
| | Longitudinal change | | | |
| | ASTM D 2671 | percent | +1, –15 | ASTM D 2671 |
| | UL 224 | percent | +3, -3 | UL 224 |
| | Eccentricity (recovered) | percent | 30 maximum | ASTM D 2671 |
| | Tensile strength | MPa (psi) | 10.3 <i>(1500)</i> minimum | ASTM D 2671 |
| | Ultimate elongation | percent | 200 minimum | ASTM D 2671 |
| | Secant modulus (as supplied) | MPa (psi) | 103 (1.5 x 10 ⁴) maximum | ASTM D 2671 |
| | Low-temperature flexibility (1 hour at -30°C/-22°F) | | No cracking | UL 224 |
| | Heat shock (4 hours at 250°C/482°F) | | No cracking | UL 224 |
| | Heat aging (7 days at 158°C/ <i>316°F</i>) | | | UL 224 |
| | Followed by tests for: | | | |
| | Tensile strength | MPa (psi) | 70% minimum of unaged specimens | UL 224 |
| | Ultimate elongation | percent | 100 minimum | UL 224 |
| | Flexibility | | No cracking | UL 224 |
| | Dielectric withstand at 2500 V | seconds | 60 minimum | ASTM D 2671 |
| | Dielectric breakdown | volts | 50% minimum of unaged specimens | ASTM D 2671 |
| | Dielectric strength | kV/mm (volts/mil) | 19.7 <i>(500)</i> minimum | ASTM D 2671 |
| | Restricted shrinkage | | Pass | UL 224 |
| Electrical | Dielectric withstand at 2500 V | seconds | 60 minimum | ASTM D 2671 |
| | Dielectric strength | kV/mm (volts/mil) | 19.7 <i>(500)</i> minimum | ASTM D 2671 |
| | Volume resistivity | ohm-cm | 10 ¹⁴ minimum | ASTM D 2671 |
| Chemical | Corrosive effect (7 days at 158°C/316°F) | | No corrosion | ASTM D 2671 |
| | Copper stability (7 days at 158°C/316°F) | | No brittleness, glazing, cracking, or severe discoloration of tubing. No pitting or blackening of copper. | ASTM D 2671 |
| | Followed by test for: | | | |
| | Ultimate elongation | percent | 100 minimum | ASTM D 2671 |
| | Flammability | | Pass | UL 224, VW-1 |

Note: Consult UL224 for specific details about test procedures.

 $\label{thm:continuous} \textit{Users should independently evaluate the suitability of the product for their application.}$



800.633.6339 www.lapptannehill.com

te.com

© 2016 TE Connectivity Ltd. family of companies. All Rights Reserved.

SWFR_X4_DS APL 7/29/2016

TE Connectivity, TE, TE connectivity (logo) and RAYCHEM are trademarks of the TE Connectivity Ltd. family of companies.

Other logos, product and/or company names might be trademarks of their respective owners.

While TE has made every reasonable effort to ensure the accuracy of the information in this document, TE does not guarantee that it is error-free, nor does TE make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. TE reserves the right to make any adjustments to the information contained herein at any time without notice. TE EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES REGARDING THE INFORMATION CONTAINED HEREIN, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. In ne event will TE be liable for any direct, indirect, incidental, special or consequential damages arising from or related to recipient's use of the information. It is the sole responsibility of the recipient of this information to verify the results of this information using their engineering and product environment. Recipient assumes any and all risks associated with the use of the information. The dimensions in this catalog are for reference purposes only and are subject to change without notice. All specifications are subject to change without notice. Consult TE for the latest dimensions and design specifications.